		Gloss				MATT			
THICKNESS (MIC)	Total	17	20	25	30	18	22	27	30
WIDTH	mm	TOLERANCE: ±2mm							
LENGTH	m	NOMINAL 2000M OR 3000M TOLERANCE:±0M-100M							
CORE		DESCRIPTION: CARDBOARD INSIDE DIAMETER:76MM WALL THICKNESS:8MM							
SPLICES		NIL PREFERRED, 2 BELOW							
TREATMENT		BOPP Side =38 Dyne / EVA Side = 52 Dyne							
SEALING STENGTH	g/15mm at 90C 2kg/m3 pressure	560	560	620	630	580	580	620	680
	kg/cm3、KSM 3001-91	MD:10.2 TD:4.9				MD:10.2 TD:4.9			
	%, KSM 3001-91	MD:19.6 TD:55.8				MD:2.36 TD:74.4			
LAMINATION TEMP RANGE	℃	85℃-110℃							
LAMINATION TEMP RANGE	kg/cm2	15mpa							
HEAT SEAL INITIATION	℃	80℃-90℃							
PACKING		INDIVIDUALLY WRAPPED, INDIVIDUALLY BOXED PALLETISED							