

Model Style 4311

Subj.758
Section 4
Page 4311

Issued: 1980-06-11
Revised: 2012-04-02

Style 4311

Multiple-Conductor Cable Using Extruded Non-Integral Jacket

RATING	125 deg C, 150 Vac, Cable flame.
INSULATION	Labeled or complying Manufacturer's AWM Procedure.
ASSEMBLY	Two or more individually insulated conductors or groups of insulated conductors cabled together. All conductors in any group twisted together. If more than one group is used, groups shall also be twisted together. The length of lay of the twisted conductors or groups is not specified. A barrier layer, if employed, may be a fibrous wrap serving, or braid; paper; nylon; oriented polyethylene terephthalate; or a thermoplastic-tape wrap. Such a barrier layer would serve to protect the cable during further processing, and is applied immediately over the twisted assembly of individual conductors or groups of conductors.
SHIELD	Optional.
COVERING	Optional. An XLPE covering may be extruded over the conductor assembly, having minimum thickness of 10 mils.

JACKET	Extruded XLPE		
	Diameter of core assembly under jacket (inches)	Minimum average thickness (mils)	Minimum thickness at any point (mils)
	1.000 or less	30	24
	1.001-1.500	45	36
STANDARD	Appliance Wiring Material UL 758.		
MARKING	General.		
USE	External interconnection of electronic equipment.		

The appearance of a company's name or product in this database does not in itself assure that products so identified have been manufactured under UL Solutions' Follow - Up Service. Only those products bearing the UL Mark should be considered to be Certified and covered under UL Solutions' Follow - Up Service. Always look for the Mark on the product.

UL Solutions permits the reproduction of the material contained in Product iQ subject to the following conditions: 1. The Guide Information, Assemblies, Constructions, Designs, Systems, and/or Certifications (files) must be presented in their entirety and in a non-misleading manner, without any manipulation of the data (or drawings). 2. The statement "Reprinted from Product iQ with permission from UL Solutions" must appear adjacent to the extracted material. In addition, the reprinted material must include a copyright notice in the following format: "©2024 UL LLC."