BEKAERT DESLEE

LABORATORY REPORT

07.10.2021

MATERIAL NUMBER: 40109706 **LOT:** 2702863

DESCRIPTION: 99044 235 TL5604 L13 0 XWAES

FABRIC: KNIT

COMPOSITION: 100% POLYESTER

FINISH: (XWAES) SOFTENER AND AEGIS

TEST:

16CFR part 1632
«STANDARD FOR THE FLAMMABILITY OF MATRESSES AND MATRESS PADS»

Material to perform the test:

- 3 test boxes,30.5 x 30.5 cm
- Cotton filling for 3 boxes (untreated).
- Foam type PU T23140 (RECTICEL) 3 pieces
- Fabric sample to test, 3 pieces of 50 x 50 cm
- 3 cigarettes on top of each sample, covered by a cotton sheet.

Conditions to approve the test:

- The mark left by the cigarette that is minor than 2.5 cm around the cigarette.
- There is no ignition with cotton.
- And if the 9 cigarettes pass the two previous statements.

9P TEST APPROVED

Results valid only to the sample delivered to the lab and to informative purpose

BekaertDeslee México

170 Carretera San Martin Texmelucan-Tlaxcala, Km 7.1 | 90120 San Felipe Ixtacuixtla | Tlaxcala | México

Tel. +52 248 48 78 300 | Fax +52 248 48 78 337 | https://www.bekaertdeslee.com

Preparation process








Ignition process













Camerino Gómez López

Quality assurance laboratory

BekaertDeslee México

170 Carretera San Martin Texmelucan-Tlaxcala, Km 7.1 | 90120 San Felipe Ixtacuixtla | Tlaxcala | México

Tel. +52 248 48 78 300 | Fax +52 248 48 78 337 | https://www.bekaertdeslee.com